

Chemical Compatibility Guide



The material contained in this guide is based upon technical data and tests made available by various chemical manufacturers and users. The purpose of this information is to provide a General Guide regarding the use of various chemicals with Cat Pumps products. This guide is not intended as an absolute materials recommendation.

Factors that may affect the material or elastomer composition in a pump using liquid chemical(s) are:

- chemical concentration
- temperature
- pump RPM
- aeration
- viscosity
- vapor point
- impurities
- mixing of chemicals
- duty cycle
- pH rating

The only reliable means of making a final selection is actual field testing under the conditions of intended use.

Cat Pumps assumes no liability for results obtained or damage incurred through the application of the data presented in this guide.

Quick Search

A	B	C	D	E	F	G	H	I	J	K	L	M
N	O	P	Q	R	S	T	U	V	W	X	Y	Z

Click on the letter to advance to that page in the document.

Legend

- A** Elastomer/material shows little or no effect after exposure to the chemical.
- B** Elastomer/material may be affected after exposure chemical. Swelling and/or a loss of physical properties is possible.
- C** Elastomer/material is effected after exposure to the chemical. Moderate or severe swelling and loss of physical properties will limit life of the elastomer/material.
- U** Elastomer/material is unsuitable when exposed to the chemical.
- *** For fluid to remain in liquid state, pressure or temperature may exceed inlet seal specifications.
- ^** A special compound may be required. Contact Cat Pumps for recommendations.

Kalrez®, Teflon® and Viton® are registered trademarks of DuPont Dow Elastomers. Chemraz® is a registered trademark of Greene, Tweed and Co. HASTELLOY 'C'® is a registered trademark of Haynes International, Inc.

Legend	Materials										Plastics			Elastomerics				
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
ACETALDEHYDE	A	A	C	C	A	A			A	A	A	A	B	A	U	U	A	A^
ACETAMIDE		U	U	C	B	A					A	B	A	A	A	B	A	A^
ACETANILIDE																		A^
ACETATE SOLVENTS (PURE)	A	A	U	A	A	A		A	A	A	A		A	A	U	U	A	A^
ACETIC ACID (GLACIAL)	C	U	U	A	C	B		A	A	A	A	C	B	A	U	C	A	A
ACETIC ANHYDRIDE	U	C	B	U	A	A		A	A	A	A	U	C	A	C	U	B	A
ACETONE	A	A	A	A	A	A		A	A	A	A	C	B	A	U	U	A	A
ACETONITRILE			A			A							B	A	U	U	A	A
ACETOPHENONE						A		U	B				U	A			A	A
ACETYL CHLORIDE		U			C	C					A	U	A	A	U	A	U	A
ACETYLENE*	U		A	A	A	A		A			A		A	A	A	A	A	A
ACETYLENE TETRABROMIDE								A					A	A		A		A
ACETYLENE TETRACHLORIDE													A	A				
ACRYLONITRILE	U	C	C		A	C			C		A		B	A	U	C	U	A^
ALCOHOL, AMYL	A	A	A	C	A	A		A	A	A	A	A	A	A	A	U	U	
ALCOHOL, BENZYL	A	A	A		A	A		A	A	A	A	A	A	A	U	A	A	A
ALCOHOL, BUTYL	A	A	U	C	A	A		A	A	B	A	A	A	A	A	A	B	A
ALCOHOL, DIACETONE	A	A	A	A		A		A	A	A	A	A		A	C	A	A	A
ALCOHOL, ETHYL	A	A	A	A	A	A		A	A	A	A	B		A	B	C	A	A
ALCOHOL, HEXYL	A	A	A	A	A	A		A	A	A	A	A		A	A	A	C	A
ALCOHOL, ISOBUTYL	A	A	C	A	A	A		A	A	A	A	A		A	B	A	A	A
ALCOHOL, ISOPROPYL	A	A	C	A	A	A		A	A	A	A	A		A	B	A	A	A
ALCOHOL, METHYL	A	A	A	A	A	A		A	A	A	A	C		A	A	U	A	A
ALCOHOL, OCTYL	A	A	A	A	A	A		A	A	A	A	A		A	B	A	C	A
ALCOHOL, PROPYL	A	A	C	A	A	A		A	A	A	A	A		A	A	A	A	A
ALKYL BENZENE														A		A		A
ALKYL CHLORIDE														A		A		A
ALUM 10%	C	C	U	A	A	C		C	C	A	C		A	A	C	B		A
ALUM 100%	C	C	U	A	U	A		C	C	A	C		A	A	A	B		A
ALUMINUM ACETATE	B	C				A		C	A		B		A	A	B	U	A	A
ALUMINUM BROMIDE														A	A			A
ALUMINUM CHLORIDE	C	C	U	A	U	U		C	A	A	A	C	A	A	A	A	A	A
ALUMINUM FLUORIDE	C			A	U	C		A	B	U		C	A	A	A	A	A	A
ALUMINUM HYDROXIDE	C	A	U	A	A	A		A	A		A	B	A	A	A	A		A
ALUMINUM NITRATE					C	B					A		A		A	C	A	A
ALUMINUM OXIDE-ABRASIVE	U	U				A								A		A		
ALUMINUM POTASSIUM SULFATE 10%			U		C	B			C	A	A	C	A		A	A	A	
ALUMINUM POTASSIUM SULFATE 100%			U		C	B			C	A	A	C	A		A	A	A	
ALUMINUM SULFATE	C	U	U	A	A	A		C	A	A	A	C	A	A	A	A	A	A
AMINES	U	U	U	B	A	A			A	B	A	U	U	A	C	U	A	A
AMMONIA ANHYDROUS LIQUID*	U	U	A	B	B	A		U	A	B	A	U	A	A	B	U	A	A^
AMMONIA LIQUORS	U	U	A	A	C	B		U	A		A	U		A	A	U	A	
AMMONIA NITRATE	U	U	A	A	C	B		U			A	C	A	A	A			
AMMONIUM BICARBONATE	U	U	C		B	A		U	B		A			A	A			A

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
AMMONIUM BIFLUORIDE	U	U	U		B	A		U	A		A	U	A	A	A	A		A
AMMONIUM CARBONATE	U	U	C	B	A	A		U	B	A	A	U	A	A	U	B	A	A
AMMONIUM CHLORIDE	U	U	U	U	U	C		U	A	A	A	B	A	A	A	A	A	A
AMMONIUM DIPHOSPHATE	U				A	A									B			
AMMONIUM HYDROXIDE (10%)	C	C	A	C	A	A		C	A	A	A	C	A	A	B	A	A	
AMMONIUM HYDROXIDE (46.5%)	U	U	A	C	A	A		U	A	A	A	C	A	A	U	B	A	A
AMMONIUM MONOPHOSPHATE	U				A	A								A				
AMMONIUM NITRATE	U	U	A	U	A	A		U	A	A	A	C	A	A	A	A	A	
AMMONIUM NITRITE	U												A	A	A		A	
AMMONIUM OXALATE	U	U	U	A	A	A			A			B	A	A	A			A
AMMONIUM PERSULFATE	U	U	U	A	A	A			A	A	A	U	A	A	A	A	A	
AMMONIUM PHOSPHATE (MONOBASIC)	C	C	C	A	C	C		C	A	A	C	B	A	A	A	A	A	A
AMMONIUM PHOSPHATE (TRIBASIC)			C	A	C	C		C	A	A	C	B	A	A	A	A	A	A
AMMONIUM SULFATE	C	B	C	C	C	C		C	A	A	A		A	A	A	U	A	A
AMMONIUM SULFIDE	U	U			C	C		U	A				A	A	A			A
AMMONIUM THIOPHOSPHATE			U	A		A				A	A				A			
AMMONIUM TRIPHOSPHATE	U				A	A									B			
AMMONIUM THIOSULFATE		U	U			A				A	A	B			A			
AMYL ACETATE	A	C		C	A	A		A	A	A	A		B	A	U	U	C	A
AMYL ALCOHOL	A	A		A	A	A		A	A	A	A		A	A	C	B	A	A
AMYL BORATE															A	A	U	
AMYL CHLORIDE	C	C		A	C	C			A	C	A	A	A	A	A	C	U	A
AMYL CHLORONAPHTHALENE														A	U	B	U	A
AMYL NAPHTHALENE														A	U	A	U	A
AMYL NITRATE														A	A			A
ANHYDROUS HYDROGEN FLUORIDE														A			A	
ANHYDROUS HYDRAZINE														A			A	
ANILINE	C	C	C	C	A	A		C	B	C	A	A	B	A	U	C	A	A
ANILINE DYES	C	C	C		A	A		C						A	U	B	A	A
ANILINEHYDROCHLORIDE	U	U			U	U			U				B	A	B	B	B	A
ANILINE OIL	A	A	A		A	A			B	U		U		A	U	C	B	A
ANISE OIL		A	A			A					A							
ANSUL ETHER															C	U	C	
ANSUL OIL															A			
ANTI-FREEZE	B	B	B	C	A	A			A		A	U	A	A	A	A	A	
ANTIMONY TRICHLORIDE					U	U				B	A		B	A		A	B	
AQUA REGIA		U			U	U			U	A	U	U	A	A	U	B	C	A
ARGON GAS*														A	A			A
AROCHLOR					C	C							A		U	A	C	A
AROMATIC HYDROCARBONS*		C	A	A		C						A	A	A	U	A	U	
ARSENIC ACID	U	C	C	U	A	A			B	B	A	U	A	A	A	A	A	A
ARSENIC COMPOUNDS	U	U			A	A		A			A			A	A			
ASKAREL														A	B	A	U	A
ASPHALT	A	A	C		A	A		A			A	A	A	A	C	A	U	A

Legend	Materials											Plastics			Elastomerics					
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	Chemical	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)	
ASPHALT TOPPING		A				A	A		A			A		A	A	C	B			
ASTM OILS NO. 1, NO. 2, NO. 3		A				A	A		A					A		A				A
AVIATION GASOLINE		A	A	A		A	A		A	A				A	A	A	A	A		
BARIUM CARBONATE			B	B	B	A	A			A	A	A	A	A	A	A	A	A	A	
BARIUM CHLORIDE		A	C	C		A	A		A	A	A	A	A	A	A	A	A	A	A	A
BARIUM CYANIDE		C	C		A	A	A							B			C	A	A	
BARIUM HYDROXIDE*		A	A	C	C	A	A		A	B	B	A	U	A	A	A	A	A	A	A
BARIUM NITRATE		U	U	A	A	A	A				A	A	A	A	A	A	A	A	A	A
BARIUM SULFATE		C	C	C	C	C	C			A	A	C	A	A	A	A	A	A	A	A
BARIUM SULFIDE		U	U	C	C	C	C		U		A	C	A	A	A	A	A	A	A	A
BEER		B	A	U	U	A	A			A	A	A	A	B	A	A	U	A	A	
BEET SUGAR LIQUORS		B	A	A		A	A				A	A	A	B	A	A	A	A	A	A
BENZALDEHYDE*		U	U	B	A	U	C			A	A	A	A	A	A	A	U	U	A	A
BENZENE		A	A	B	C	A	A			A	A	A	A	A	A	A	U	A	U	A
BENZENESULFONIC ACID																		A		
BENZINE (GASOLINE)		A	A	A		A	A		A	A		A			A	A	A	A	U	A
BENZOIC ACID		A	B	U		A	A		A	A	A	C	B	A	A	A	C	A	C	A^
BENZOL			A	A		A	A			B			A	A	A		U	A	B	
BENZYL BENZOATE																A	U	A	B	A
BENZYL CHLORIDE	U	U	U			U				C				B	A	U	A	U	A	
BICHLORIDE OF MERCURY															A	A				
BLACK SULFATE LIQUID	C								C					A	A	A	A			
BLEACH LIQUOR	C	C			A	C			C						A	U	A	A	A^	
BOILER FEED WATER	A	A			A	A		A				A		A	A	C	U			
BONE OIL		A	A			A						A				A	A			
BORAX (SODIUM BORATE)	B	A	A	C	A	A				A	B	A	A	A	A	B	A	A		
BORIC ACID	A	B	U		B	A		A	A	A		C	A	A	A	A	A	A	A	
BRAKE FLUID	A	A	A		A	A		A	A			A			A	U				
BRINE – ABRASIVE	A	A	U		A	A		A	A			A			A	A	A	A	A	
BROMINE	C	C	U	U	U	U			C	A	A	U	U	A	A	U	A	U	A	
BROMINE TRIFLUORIDE																U	U	U	A^	
BROMINE WATER						U		A	A				U	A		U	A	B	A	
BROMOBENZENE														A		U	A	U		
BUNKER 'C' FUEL OIL	A	A			A	A		A				A			A	A	A	U	A	
BUTADIENE RHTEMP*	A	C	C	C	U	U		U			A	U	A	A	C	U	A	C	A	
BUTANE*	A	A	C	C	A	A		A	C	A		A	A	A	A	A	A	U	A	
BUTTER		U	U		B	A						A	A		A	A	A	A		
BUTTERMILK		U	U		A	A			A			A		A	A	A	A			
BUTYL ALCOHOL														A		A	A	B	A	
BUTYL ACETATEROOM TEMP.	A	A	A	A	C	C		A	A	A		A	A	U	A	U	U	C	A	
BUTYL ACRYLATE														U			U	U		
BUTYL AMINE						A								U	A	C	U	B	A^	
BUTYL BENZOATE																U	A	B	A	
BUTYL CARBITOL														B		A	A	A		

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELTRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
BUTYL CELLOSOLVE													B	A	C	U	A	A
BUTYLENE	A	A	A	A	A	A					A	A	A	A	A	A	U	
BUTYLOLEATE														A	U	A	B	A
BUTYL PHTHALATE									A				C	A			A	
BUTYL STEARATE													A	A	B	A	C	A
BUTYRALDEHYDE		U	A			U							B	A	U	U	B	A^
BUTYRIC ACID	C	C	U		C	C		C	A	A	U	C	A	A	C	B	B	A
CALCIUM ACETATE													A	A	B	U	A	A
CALCIUM BISULFATE	C	C	U		A	A					A		A	A	A	A	U	
CALCIUM BISULFIDE	U	C			C	C		U	A	A	A	U	A	A	A	A	U	A
CALCIUM BISULFITE	C	C			U	A		C	A	A	A	U	A	A	U	A	U	A
CALCIUM CARBONATE SLURRY	A	A	U		A	A		A	A	A	A	A	A	A	A	A		
CALCIUM CHLORATE (DILUTE)		C			C	A			A			U		A		A		
CALCIUM CHLORIDE	C	A	C		A	A		A	A	A	A	U	A	A	A	A	A	A
CALCIUM HYDROXIDE 10%	A	B			A	A		A	A	A	A	U	B	A	A	A	A	A
CALCIUM HYDROXIDE 50%						C			A		A		C	A				A
CALCIUM HYPOCHLORITE	C	C	U		C	C		C	B	A	C	U	C	A	B	A	A	A
CALCIUM NITRATE						C			B		A	A	A	A	A	A	A	A
CALCIUM PHOSPHATE											A		A	A	A			A
CALCIUM SALTS — ABRASIVE													A	A	A			A
CALCIUM SULFATE	A	A	A		A	A			B	A	A	U	A	A	A	A	A	A
CALCIUM SULFIDE													A		A	A	A	A
CANE SUGAR LIQUORS		A	A		A	A			A		A	A	A	A	A	A		
CARBAMATE															C	A	B	A
CARBITOL													A	A	B	B	B	A
CARBOLIC ACID (PHENOL)	C	C	U		B	A		C	A	A	U	U	B	A	U	A	B	A
CARBON BISULFIDE		B			A	B					A	A	C	A	C	A	U	A
CARBON DIOXIDE*	A	A	U		A	A		A	A	A	A	A	A	A	A	A	B	A
CARBON DISULFIDE	C	C	A	C	A	A		C	A	B	C	A	U	A	U	A	U	A
CARBONIC ACID	A	A	U		A	B			A	B	A	B	A	A	B	A	A	A
CARBON MONOXIDE*		C	U		A	A			A		A	A	A	A	A	A	A	A
CARBON TETRACHLORIDE*	A	A	C	U	A	A		A	A	A	A	B	B	A	C	A	U	A
CASTOR OIL	A	A	A		A	A		A		A	A	A	A	A	A	A	B	A
CATSUP		C	U		A	A					A		A		A	A	C	
CELLOSOLVE						A			A				B	A	U	C	B	A
CELLOSOLVE ACETATE													A		U	U	B	A
CELLULOSE														A	A			
CELLULUBE		A	A		A	A									U	A	A	
CHINA WOOD OIL (TUNG OIL)					A	A			A					A	A	A	C	A
CHLORIC ACID					U	U			A			U	B	A				
CHLORINATED LIME		U	U		A	A							C	A	C			A
CHLORINATED SALT BRINE — ABRASIVE					C	C			A	A		U	A	A	A	A	C	A
CHLORINATED SOLVENTS	A	A				C							A	A		A		A
CHLORINATED BIPHENYL													B	A		A		A

Legend	Materials											Plastics			Elastomerics			
Chemical	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD, CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®, CHEMREZ® (KPFE)
A - GOOD																		
B - FAIR																		
C - QUESTIONABLE																		
U - UNSATISFACTORY (See Legend Page for Details)																		
CHLORINE (ANHYROUS LIQUID)	C	C	C		C	C		C	A	A	U	A	C	A	U	B	C	B
CHLOROACETIC ACID		U	U		U	U			A	A		U	C	A	U	A	B	
CHLOROACETONE		U	U			A								A	U	U	A	A
CHLOROBENZENE	A	A	U	C	A	A			A	A	A	A		A	U	A	U	A
CHLORO BROMOMETHANE		U	U			A								A	U	C	B	A
CHLOROBUTADIENE		U	U			A								A	U	A	U	A
CHLORODECANE															U	A	U	A
CHLOROFORM*	A	A	U	C	A	A		A	A	A	A	B	B	A	U	A	U	A
CHLORONAPHTHALENE															U	A	U	
CHLOROPHENOL 5%						A			A				A	A				A
CHLOROSULFONIC ACID			U	U		U			B	A	C	U	U		U	U	U	A
CHLOROTOLUENE														A	U	A	U	A
CHLOROX (BLEACH)		A	U	C	A	A			A		A	U	A	A	C	C	B	
CHOCOLATE SYRUP		U	U		A	A					A	A	A	A	A	A		
CHROMIC ACID 5%	U	U	U		C	C		U	A	A	C	B	B	A	U	A	C	A
CHROMIC ACID 30%	U				C	C		U	A	A	U	C	B	A	U	A	C	A
CHROMIC ACID 50%	U	U	U		C	U		U	B	A	U	U	C	A	U	A	C	A
CIDER		A	U		A	A					A	B		A	A	A		
CINNAMON OIL		A			A	A					A	U	A			A		
CITRIC ACID	U	C	U		A	A		U	A	A	C	B	A	A	A	A	A	A
CITRIC OILS	U	U	U		A	A					A	B		A	A	A		
CITRUS PECTIN LIQUOR					A	A								A	A	A		
CLOVE OIL		U	U		A	A			A		A			A	A	A		
COAL TAR														A	A	A	U	A
COBALT CHLORIDE														A	A	A	A	A
COCOA BUTTER														A	A			
COCONUT OIL	A	A	A		A	A			A		A	A	A	A	A	A	C	A
COD LIVER OIL	U	U			A	A			A		A	B			A	A	A	A
COFFEE		A	C		A	A			A		A			A	A	A		
COPPER ACETATE						A			A				A	A	B	U	A	A
COPPER AMMONIUM ACETATE														A	A			A
COPPER CHLORIDE	C	C	U		U	U		C	A	A	A	B	A	A	A	A	A	A
COPPER CYANIDE	C	C	U		A	A			A	A	A	B	A	A	A	A	A	A
COPPER FLUOBORATE		U	U		U	U			B			B	A	A	B	A		
COPPER NITRATE	C	C			A	A		C	A	B	A	U	A	A	A	A		A
COPPER SALTS – ABRASIVE													A	A	A			A
COPPER SULFATE (5% SOLUTION)	C	U	U		A	A		C	A	A	A	U	A	A	A	A	A	A
CORN OIL		A	A		A	A							A	A	A	A		
COTTON SEED OIL	A	A	A		A	A		A	A	A	A	B	A	A	A	A	B	A
CREAM	U	U	U		A	A					A	A		A	A	A		
CREOSOLS	C	C	C		A	A			B	B	A	U	A	A	C	B		
CREOSOTE OIL	A	A	A		A	A		A	A	A	A	U	A	A	A	A	U	A
CRESYLIC ACID	C	C	C		A	A			B	A	A	U	B	A	U	B	U	A
CRUDE OIL					A	A			A				A	A	C	A	U	A

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical													A			A		
CUMENE													A			A		
CUPROUS AMMONIA ACETATE														A	A			
CUTTING OIL (WATER SOLUBLE)	A	A	A		A	A		A			A		A	A	C	A		
CUTTING OIL (SULFUR BASE)	A	A	A		A	A		A			A		A	A	A			
CYANIC ACID		U	U		A	A									C	A		
CYANIC COMPOUNDS														A	A			
CYANOGEN														A			A	
CYCLOHEXAMONE														A			A	
CYCLOHEXANE		U	A	A		A			A	A	A	A	A	A	A	A	U	A
CYCLOHEXANOL						A			A				A	A	B	A	C	A
CYCLOHEXANONE						A			A				C	A	U	U		
CYCLOHEXYLAMINE														A	A		A	
CYMENE													B			A		
DECALIN															U	A		
DECANE														A	A			
DEIONIZED WATER	U				A	A		U			A			A	A	A		A^
DENATURED ALCOHOL														A	A	A	A	A
DETERGENT WATER SOLUTIONS		A		A	A	A			A	A	A	A		A	A	A	A	
DEVELOPING FLUIDS															A	A	B	
DIACETONE														A	U	U	A	A
DIACETONE ALCOHOL	A	A			A	A		A						A	U	U	A	A
DIAMYLAMINE														A			A	A^
DIBENZYL ETHER		U	U			A								A	U	U	B	A
DIBENZYL SEBACATE														A	U	B	B	A
DIBROMOETHYL BENZENE														A	U	B	U	A
DIBUTYL AMINE															U	U	C	A^
DIBUTYL ETHER		U	U			A								A	U	C	C	A
DIBUTYL PHTHALATE															U	C	B	A
DIBUTYL SEBECATE															U	B	B	A
DICHLOROBENZENE														A	U	A	U	A
DICHLOROBUTANE														A		A		A
DICHLOROETHANE					A	A			A	B		A		A	C	A		A
DICHLOROHEXYLAMINE														A	C	U	U	A^
DICHLOROISOPROPYL ETHER															U	C	C	A
DICHLOROPENTANE														A	C	A		
DIESEL FUEL	A	A	A	A	A	A		A	A	B	A	A		A	A	A	U	A
DIETHANOLAMINE											A			A	A		A	A^
DIETHYLAMINE		A				B				U	A	B			C	U	B	
DIETHYL ANILINE														A			A	
DIETHYL BENZENE														A	U	A		
DIETHYL CARBONATE														A			A	A
DIETHYL ETHER*	C	C			C	C								A	U	U	U	A
DIETHYL FORMALDEHYDE														A			A	
DIETHYL HYDRAZINE														A			A	

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
DIETHYL MALEATE														A			A	
DIETHYL SEBACATE														A	B	B	B	A
DIETHYL SULFATE														A	A			A
DIETHYLAMINE		A				A								A	B	U	B	A^
DIETHYLBENZENE															U	A	U	A
DIETHYLENE GLYCOL	C	C	A		C	B			B	A	A	A		A	A	A	A	A
DIETHYLENE TRIAMINE														A			A	A^
DHSOBUTYL KETONE														A			A	A
DHSOBUTYLENE					A									A	B	A	U	A
DHSOOCTYL SEBECATE														A		A		
DHSOPROPYL BENZENE														A		A		
DHSOPROPYL KETONE														A	U	U	A	A
DIMETHYL ANILINE														A	C	U	B	A
DIMETHYL ETHER															A	A	U	A
DIMETHYL-FORMAMIDE						A			A					A	B	U	B	A
DIMETHYL PHTHALATE						A			A					A	U	B	B	A
DINITROCHLORO BENZENE														A		A		A
DINITROTOLUENE					A	A								A	U	U	U	A
DIOCTYL PHTHALATE															C	B	B	A
DIOCTYL SEBECATE															U	B	B	A
DIOXANE															U	U	B	A
DIOXOLANE															U		B	
DIPENTENE															B	A	U	A
DIPHENYC, CHLORINATED														A		A		
DIPHENYC, OXIDES – ABRASIVE	A				A	A					A			A	A	A		
DIPHENYL															U	A	U	A
DIPHENYL OXIDE		A	A		A	A			B	A	A	U			U	A	U	A
DOWTHERM® FLUIDS					A	A									U	A	U	A
DRY CLEANING FLUIDS															C	A	U	A
DYES, ABRASIVE		C			A	A						C			U	B		
DYES, WATER BASED		C			A	A						C		A		A		
EMBALMING FLUID		A			A	A								A	A			
EPICHLOROHYDRIN						A								A	U	U	B	A^
EPSOM SALTS (MAGNESIUM SULFATE)	A	A	A	B	A	A		A	B	A	A	B		A	A	A	U	A
ETHANE GAS*		A			A	A					A			A	A	A	U	A
ETHANOLAMINE		A		C	A	A			B	B	A	U		A	B	U	B	A^
ETHER COMPOUNDS	A	A	C		A	A		A	B	A	A	A		A	U	U	A	A
ETHYL ACETATE	A	A	A	C	A	A		A	B	A	A	A		A	U	U	B	A
ETHYL ACETOACETATE														A	U	U	B	A
ETHYL ACRYLATE		B	U			A								A	U	U	B	A
ETHYL ALCOHOL	A							A	A					A	C	C	A	A
ETHYL AMINE														A				
ETHYL BENZENE														A	U	A	U	A
ETHYL BENZOATE														A	U	A	A	A

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
ETHYL BROMIDE														A				A
ETHYL CELLOSOLVE														A	U	U	U	A
ETHYL CELLULOSE														A	B	U	B	A
ETHYL CHLORIDE	A	A	C	U	A	A		A	B	A	A	A		A	A	A	C	A
ETHYL CHLOROCARBONATE														A	U	A	B	A
ETHYL CHLOROFORMATE														A	U	A	B	A
ETHYL DICHLORIDE														A	U	A	C	
ETHYL ETHER*	A	A	C		A	A								A	C	U	C	A
ETHYL FORMATE														A	U	A	B	A^
ETHYL HEXANOL														A	A			A
ETHYL MERCAPTAN														A	U	B	C	A
ETHYL OXALATE														A	U	A	A	A
ETHYL PENTACHLOROBENZENE														A	U	A	U	A
ETHYL PYRIDRINE														A				A
ETHYL SILICATE														A	A	A	A	A
ETHYL SULFATE		A			U	U					A			A	A	A		
ETHYLENE GAS*														A	A	A	B	A
ETHYLENE BROMIDE														A			A	
ETHYLENE CHLORIDE	C	A	C	C	A	A		C	A	B	C	A		A	U	B	C	A
ETHYLENE CHLOROHYDRIN														A	U	A	B	A
ETHYLENE DIAMINE						A			A					A			A	
ETHYLENE DIBROMIDE														A		A		
ETHYLENE DICHLORIDE	C	C	A	C	A	A			C	B	C	B			U	A	C	A
ETHYLENE GLYCOL – ANTIFREEZE	A	A	A	C	A	A		A	A	A	A	B		A	A	A	A	A
ETHYLENE OXIDE	A	A	U		C	A					A			A	U	U	C	A^
ETHYLENE TRICHLORIDE														A	U	A	C	A
ETHYLENEDIAMINE															A	U	A	B^
FATTY ACIDS	C	C	C		A	A			A	A	A	A		A	B	A	C	A
FERRIC CHLORIDE	U	U	U		U	U			A	A	A	U		A	A	A	A	A
FERRIC NITRATE		U			A	A			A	A	A	U		A	A	A	A	A
FERRIC OXIDE – ABRASIVE	U				U	U		U			U			A		A		
FERRIC SULFATE	U	U	U		C	C			A	A	U	U		A	A	A	A	A
FERROUS CHLORIDE	C	C	U		U	U		C	B	A	B	U		A	A	A		A
FERROUS SULFATE	C	C	U	U	A	A		C	A	A	A	U		A	A	C	A	A
FIBERGLASS RESIN-UNKOWN VARIABLES	C				U	U		C			U							
FISH OIL															A	A		
FLUORINATED CYCLIC ETHER														A			A	
FLUORINE		U	U	U	U	U			A	U				C		B	A	
FLUORO BENZENE														A		A		
FLUOROLUBE®															A	B	A	B^
FLUOROBORIC ACIDS		U	U		C	C			A	U	U			A	B	A	A	A^
FLUOROCARBON OILS																	A	
FLUROSILICIC ACID	C		U		C	U			B	U	A			A	A	A	B	A
FORMALDEHYDE (FORMALINE)*	A	A	C	A	A	A		A	A	B	A	A		A	C	U	A	A^

Legend	Materials										Plastics			Elastomerics				
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
FORMIC ACID	C	C	U	U	C	C		C	A	C	A	U		A	U	A	A	
FREON® 11*	U	B	C	B	C	C		U	A	B	A	U		A	C	C	U	
FREON® 12 (WET)*	U	B	B		U	U			A	B	A	B		A	A	A	B	
FREON® 13*															A	A	A	
FREON® 13B1*																		
FREON® 21															U	U	U	
FREON® 22*		B	C			A			A	A	A	A		A	U	U	A	A^
FREON® 31*															U	U	A	
FREON® 32*															A	C	A	
FREON® 112*															B	A	U	
FREON® 113*		B				A			A	C	A	A		A	A	C	U	
FREON® 114*															A	B	A	
FREON® 114B2*															B	B	U	
FREON® 115*															A	B	A	
FREON® 142b*															A	U	A	
FREON® 152a*															A	U	A	
FREON® 218*															A	A	A	
FREON® 502*															B	B		
FREON® C316*															A		A	
FREON® C318*															A	A	A	
FREON® BF*															B			
FREON® MF*															A			
FREON® TA*															A	C	A	
FREON® TC*															A	A	B	
FREON® TF*	U	A			C	C		U	A	B	C	A		U	C	C	U	
FREON® TMC*															B	A	B	
FREON® T-P35*															A	A	A	
FREON® T-WD602*															B	A	B	
NOTE: INLET SEALS WILL HAVE LIMITED LIFE WHEN COMPRESSED GASES ARE PUMPED																		
FRUIT JUICES		C	U	U	A	A			A	A	A	A		U	A	A		
FUEL OIL	C	A	A		A	A		C	A	A	A	B		A	A	A	U	A
FUMARIC ACID														A	A	A	B	A
FURAN, FURFURAN	A	A	A	A	A	A		A				U		A	U	A	C	A
FUFURAL		A	A		B	B			B	A	A	U		A	U	U	B	
GALLIC ACID	C	C	U	U	C	C			A	A				A	B	A	B	A
GASOLINE 'HEAT' (LOW LUBRICITY)	A	A	A		A	A		A	A	B	A	B		A	C	A	U	A
GELATIN	C	A	U	U	A	A			A	A	A	A		A	A	A	A	
GINGER OIL		U	U		A	A					A	A			A	A		
GLACIAL ACETIC ACID			U						A					A	C	C	A	A
GLUCOSE	A	A	B	B	A	A		A	A	A	A	A		A	A	A	A	A
GLUE SIZING	A	A	A	A	A	A			A	U	A	A		A	A	A	A	A
GLYCERIN (GLYCEROL)	A	A	B	B	A	A		A	A	A	A	A		A	A	A	A	A
GLCOLIC ACID						A			A	B		A			A	A	A	
GLYCOLS														A	A	A	A	A

Legend	Materials										Plastics			Elastomerics				
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
GOLD MONOCYANIDE		U	U		A	A					A	A		C	A	A		
GRAPEFRUIT OIL		U	U		A	A								A	U			
GRAPE JUICE		C	U		A	A				A	A	A		A	C	A		
GREEN SULFATE LIQUORS															B	A	A	
HEPTANE	A	A	A	B	A	A			A	A	A	A		A	A	A	U	A
HEXACHLORO ACETONE														A			A	A
N-HEXALDEHYDE														A	U	U	A	A^
HEXAMINE														A			A	
HEXANE		A	A	B	A	A			A	A	A	A		A	A	A	U	A
HEXONE											A			A		A	A	A
HEXYL ALCOHOL	A	A						A						A	A	A	C	A
HONEY		A	A			A			A		A			A		A		
HYDRAULIC FLUIDS	A	A	A		A	A			A		A	B		A	C	A	U	A
HYDRAZINE (WATER BASED)		U	C		A	A						B		C	B	U	A	A
HYDRAZINE (ALCOHOL BASED)		U	C		A	A						B		C	B	U	A	A
HYDROBROMIC ACID	C	U	U	U	U	U		C	A	A	A	U		A	v	A	A	A
HYDROCARBONS, LIGHT*	A	A						A						A	A			A
HYDROCHLORIC ACID (MURATIC ACID)	U	U	U		C	C		U	A	C	C	C		A	C	A	A	A
HYDROCHLORIC ACID (30-37%)	U	U	U		U	U		U	B	C	U	C		A	C	A	A	A
HYDROCYANIC ACID	U	U	U	C	A	A		U	A	A	A	B		A	B	A	A	A
HYDROFLUORIC ACID (50% OR LESS)	U	U	U		U	U		U	B	U	U	U		C	U	B	C	A
HYDROFLUORIC ACID (50% OR MORE)	U	U	U		U	U		U	B	U	C	U		A	U	A	C	A
HYDROFLUOSILICIC ACID		U	U		U	U			C	B	A	B		A	C	A	A	
HYDROGEN GAS*	A	A	B	B	A	A		A	A	A				A	A	A	A	
HYDROGEN BROMIDE*														A	A			A
HYDROGEN CHLORIDE*	C	C			C	C		C						A	A	A	A	A
HYDROGEN PEROXIDE*	C	C	U	U	C	C		C	A	B	C	U		A	B	B	C	A
HYDROGEN SULFIDE*	U	U	U		C	C		C	A	A	C	C		A	U	U	A	A^
HYDROQUINONE														A	U	B	B	A
HYDROXYACETIC ACID		U	B							B	A	A			A	A	A	
INK (MAY BE ABRASIVE)	C	C	U	U	A	A					A	A		U	A	A		
INSECTICIDES (MAY BE ABRASIVE)														A		A		
IODINE	U	U	U		U	U			A	A	A	U		A	B	A	B	A
IODINE PENTAFLUORIDE		A				B			A						U	U	U	B
IODOFORM														C			A	
IRON SULFATE														A	A			
ISO-BUTANE*														A	A			A
ISO-BUTYL ALCOHOL	A	A						A						A	B	A	A	A
ISO-BUTYL METHYL KETONE														A			A	A
ISO-BUTYL N-BUTYRATE														A	A		A	
ISO-BUTYLENE*														A				A
ISO-BUTYRALDEHYDE														A			A	
ISO-OCTANE														A	A	A	U	A
ISO-PENTANE	A				A	A		A						A	A	A		A

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
ISOPHORONE															U	U	A	
ISOPROPANOL														A	B	A	A	A
ISOPROPYL ACETATE		B			C	B			B		A	U		A	U	U	B	
ISO-PROPYL ALCOHOL		A			A	A			A	A	A			A	B	A	A	A
ISO-PROPYL BENZENE														A		A		
ISOPROPYL CHLORIDE														A	U	A	U	A
ISO-PROPYL ETHER		A		A	A	A			A		A	U		A	B	U	U	A
ISOTANE											A			A	A	A		
JET FUEL (JP-1 THRU JP-6)	A	A	A	A	A	A		A	A	A	A	A		A	A	A	U	A
KEROSENE	A	A	A	B	A	A		A	A	A	A	A		A	A	A	U	A
KETONES		A	A	A	A	A			A	A	C	U		A	U	U	U	
LACQUERS	C	A	C	C	B	B		C	A		A	U		A	U	U	U	A
LACQUER THINNERS		A	C		A	A			A	C		U		A	U	U	U	
LACTIC ACID (COLD)	C	C	U	U	A	A		C	A	A	A	B		A	B	A	A	A
LACTIC ACID (HOT)	C	C	U	U	A	A		C	A	A	A			A	C	A	U	A
LANOLIN									A		A					A		
LARD (ANIMAL FAT)		A	A	C	A	A			A	A	A	B		A	A	A	B	A
LATEX — ABRASIVE	A	A			A	A			A		A	C		A	A	A	A	
LAVENDER OIL															B	A	U	
LEAD ACETATE		A	A	U	B	A			B	A	A	U		A	B	U	A	A
LEAD NITRATE														A	A		A	A
LEAD SULFAMATE					C	C								A	B	A	v	A
LEMON OIL		A			A	A					A	U		A		A	U	
LIGNIN LIQOUR		A			A	A								A	A	A		
LIGROIN		A				A						B			A	A	U	
LIME		A	A		A	A				A	A	B		A	A	A	U	
LIME BLEACH															A	A	A	
LIME SULFUR															U	A	A	
LINDOL																B	A	
LINOLEIC ACID															B	B	U	
LINSEED OIL	A	A	A		A	A		A	A	A	A	A		A	A	A	C	A
LIQUID PETROLEUM GAS (LOW SEAL LIFE)*														A	A	A	U	A
LIQUOR-PULP MILL														A	A			
LIQUOR SULFATE														A	A			
LITHIUM BROMIDE	A		A											A	A	A		A
LITHIUM CHLORIDE	C	C			A	A								A	A			A
LITHIUM HYDROXIDE	U	U			C	C								A				A
LUBRICATING OILS	A	A	A		A	A		A	A	A	A			A	A	A	U	A
LYE															B	B	A	
MAGNESIUM ACETATE														A	A			
MAGNESIUM CARBONATE		A			A	A			A	A	A	A		A	A	A	A	
MAGNESIUM CHLORIDE	A	A	U	C	B	B		C	A	A	A	A		A	A	A	A	A
MAGNESIUM HYDROXIDE	B	C	B	B	A	A		A	A	A	A	A		A	B	A	A	A
MAGNESIUM NITRATE		U	U		A	A			A	A	A	A		A	A	A	A	

Legend	Materials										Plastics			Elastomerics				
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
MAGNESIUM OXIDE – ABRASIVE		A	A		A	A					A	A		A	A	C	A	
MAGNESIUM SULFATE	A	A	A	B	A	A		A	B	A	A	A		A	A	A	U	A
MAGNESIUM SULFITE															A			A
MALEIC ACID	C	C	C	B	C	C			A	A	A	A		A	U	A	B	A
MALEIC ANHYDRIDE									A		A	U		A	U	U	B	A
MALEIC HYDRAXIDE											A			A	A			
MALT LIQUORS														A	A	A		
MANGANESE CHLORIDE						A								A	A			
MANGANESE NITRATE														A	C	C		
MAYONNAISE		U	U		C	A			A					A	A	A		
MELAMINE RESINS	U	U	U		C	C					A			A	C	A	A	
MERCURIC CHLORIDE (DILUTE SOLUTION)	U	U	U	U	U	U		U	B	A	A	B		A	A	A	A	A
MERCURIC CYANIDE		U			B	A			A	A	A			A	A			
MERCURIOS NITRATE						A					A	A		A	A	A		A
MERCURY	U	U	A	U	A	A		U	A	A	A	A		A	A	A	A	A
MERCURY SALTS – ABRASIVE	U	U						U						A	A			
MESITYL OXIDE															U	U	B	
METHACRYLIC ACID															U	U	B	A
METHANOL	A	A	A	B	A	A		A	A	B	A	A		A	A	B	A	A
METHYL ACETATE		A			A	A			A		A	B		A	U	U	B	A
METHYL ACETONE		B	A	A	A	A					A	U		A	U	U		
METHYL ACRYLATE											A	B		C	U	U	B	A
METHYL ALCOHOL	A	A	A	B	A	A		A	A	B	A	A		A	A	B	A	A
METHYLAMINE		U	A			A									B	C		
METHYL BROMIDE					A	A					A	U		A	C	A	U	
METHYL BUTYL KETONE		A			A	A					A	U		A	U	U	A	A
METHYL CELLUSOLVE		A			A	A					A	U		A	C	B	B	A
METHYL CHLORIDE	C	C	A		C	C		C	A	A	A	U		A	U	B	C	A
METHYL CHLOROSILANCES														A		A		A
METHYL CYCLOPENTANE						A								A	U	B	U	A
METHYL DICHLORIDE											A	U			U	A	U	
METHYL ETHER*														A	A	A	U	A
METHYL ETHYL KETONE		A	A		A	A			A	A	A	B		A	U	U	A	A
METHYL ETHYL KETONE PEROXIDE														A				A
METHYL FORMATE														A	U		B	A
METHYL ISOBUTYL KETONE		C	A		A	A			A	A	A	U		A	U	U	C	A
METHYL ISOPROPYL KETONE		A			A	A			A		A	U		A	U	U	B	A
METHYL METHACRYLATE											A	U		A	U	U	U	A
METHYL OLEATE														A	U	B	B	A
METHYL SALICYLATE														A	U		B	A
METHYLENE BROMIDE			A			A								A	B	A	U	A
METHYLENE CHLORIDE	U	A	A		C	C		U	A	B		A		A	U	B	C	A
METHYLENE DICHLORIDE						A								A		A		
MILK	C	C	U	U	A	A			A	A	A	A		A	A	A	A	

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
MINE WATER (HARDNESS AFFECTS WEAR)	A	A			A	A		A	A					A	A			
MINERAL OIL	A	A	A	B	A	A		A	A	A	A	A		A	A	A	C	A
MINERAL SPIRITS	A				A	A		A			A			A	A	A		
MOLASSES	A	A	A	A	A	A		A	A		A	A		A	A	A		
MONO BROMOBENZENE														A		A		
MONO CHLOROBENZENE														A	U	C	U	
MONO ETHANOLAMINE														A	U	U	A	
MONOMETHYL ANILINE																		
MONO METHYLETER														A	A	A	A	
MONOVINYL ACETYLENE															A	A	A	
MURIATIC ACID (30%)	U	U			U	U		U	B					A	A	A		
MUSTARD		B	C	B	A	A			A	A	A	C			B	A		
NAPTHA	C	C	B	B	A	A			A	A	A	U		A	B	A	U	A
NAPTHALENE	C	C	B	A	A	A			A	A	A	U		A	U	A	U	A
NAPTHENIC ACID	C	C			A	A								A	A	A	U	
NATURAL GAS*	A	A				A									A	A	U	A
NEATSFOOT OIL															A	A	B	
NEVILLE ACID															C	A	B	
NICKEL ACETATE		A	U		C	A			A						B	U	A	A
NICKEL CHLORIDE — ABRASIVE	A	U	U		C	C			A	A	A	A		A	A	A	A	A
NICKEL SULFATE	C	C	U	U	C	C		U	B	A	A	A		A	A	A	A	A
NICKEL NITRATE						A			A	B	A	B		A	A	A		A
NITRIC ACID, DILUTE	U	U	U	U	C	C		U	A	A				A	U	A	B	A^
NITRIC ACID (5-10% SOLUTION)	U	U	U	U	C	C		U	A	A	C	U		A	U	A		
NITRIC ACID (50% SOLUTION)	U	U	U		C	C		U	A	A	C	U		A	U	C	U	A
NITRIC ACID, RED & WHITE FUMING	U	U	U		U	U		U	A			U		A	U	C		
NITROBENZENE	C	C	B	B	A	A			B	A	A			A	U	B	A	A
NITROBENZINE		C	C		B	A			U	A	A	B			U	A	C	
NITROETHANE														A	U	U	B	A
NITROMETHANE														A	U	U	B	
NITROGEN GAS*	A				A	A								A	A			
NITROGEN TETRAOXIDE															U	U	C	
NITRO METHANE									A					A	U	U	B	A
NITROPROPANE														A		U		A
NITROUS ACID		A			A	A					A	U				A	A	
OCTACHLOROTOLUENE															U	A	U	A
OCTADECANE															A	A	U	A
N-OCTANE															B	A	U	A
OLEIC ACID	C	B	C	C	A	A		A	B		A	C		A	C	B	U	A
OLEAM	C	C		B	B	A			B	U	A	U		A	C	A	U	
OLIVE OIL		A	A	B	A	A			A	A	A			A	A	A	B	A
ORANGE OIL		A			A	A			A	A	A				A	A		
ORTHO-DICHLORO BENZENE														A		A		
ORTHOCHLORO ETHYL BENZENE														A		A		

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
ORTHOCIDE															A			
ORTHOCRYL															A			
OXALIC ACID	A	C	U	U	B	B		C	A	C	A	C		A	U	A	A	
OXYGEN (LIQUID)*		A			A	A		A						C	B	A	A	A^
OZONE*														C	U	A	A	A^
PAINT (WITH XYLENE)	A	A	A		A	A		A			A			A	C	C		
PAINT THINNER	A													A		A	U	
PALM OIL	A	A	A		A	A				A	A	U			A	A		
PALMITIC ACID															A	A	B	
PARAFFIN (MOLTEN)	A	A	B	B	A	A		A	A		A	A		A	A	A	U	
PARA-DICHLOROBENZENE														A		A		
PARAFORMALDEHYDE														A			A	
PEANUT OIL	A	A	A		A	A				A	A	U		A	A	A	C	A
PECTIN LIQOUR														A	A			A
PENTANE		A	B	B	C	C			B		A	B		A	A	A	U	A
PENTACHLORO PHENOC														A		A		
PERCHLORIC ACID	U	U			U	U		U						A	U	A	B	A^
PERCHLOROETHYLENE	A	A	B	B	A	A			A	A	A	A		A	C	A	U	
PETROLATUM		A	C	C		A			A		A	B		A	A	A	A	A
PETROLEUM ETHER*						A								A			A	
PHATHALIC ANHYDRIDE		B	C	C	A	B			A					A	C	A		
PHENOL		C	U		B	A			A	A	A	U		A	U	A	B	A
PHENYL BENZENE														A	U	A	U	A
PHENYL ETHYL ETHER*														A	U	U	U	A
PHENYL HYDRAZINE														A	U	A	B	A
PHORONE															U	U	C	A
PHOSPHORIC ACID, CRUDE	U	U	U	U	U	U		U	A	C	C	U		A	U	A	B	A
PHOSPHORIC ACID (50%)	U	C	U		C	C		U	A	A	C	U	A	A	U	A	A	A
PHOSPHORIC ACID, PURE	U	U	U		C	C		U	A	B	U	U		A	U	A	A	A
PHOSPHORIC ANHYDRIDE	U				A	A								A	U	U		
PHOSPHOROUS TRICHLORIDE						A			A					A	U	A	A	A
PHOTOGRAPHIC DEVELOPER		U	U		C	A			A	A	A	A		A	A	A	B	
PICRIC ACID	U	U	A		A	A			A	A		A		A	B	A	B	A
PINENE														A	B	A	U	A
PINE OIL		U	C		A	A				A	A	U			B	A	U	
PIPELINE CLEANER		A	A		A	A			B	A	A			A	U	A		
PIPERIDINE															U	U	U	
PLATING SOLUTIONS:																		
ACID FLUOBORATE BATH						U			A	U					B	A		
ACID SULFATE BATH						U			A	A					A	A		
ANTIMONY BATH		A	A		A	A			A	A	A	A		A	A	A		
ARSENIC BATH		A	A		A	A			A	A	C	A		A	A	A		
BARREL CHROME BATH		U	C			U			C	C	A	U		A	U	A		
BARREL COPPER BATH						A			A	A					A	A		

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ® ,CHEMREZ® (KPFE)
Chemical																		
BLACK CHROME BATH		C	A			U			C	A	A	U		A	U	C		
BRASS BATH-REGULAR		A	A		A	A			A	A	C	A		A	A	A		
BRASS BATH-HIGH SPEED		A	A			A			A	A	U	A			A	A		
CHROMIC-SULFURIC BATH		C	A			U			U	A	A	U			U	A		
COPPER-CADMIUM BRONZE BATH		A	A		A	A			A	A	C	A		A	A	A		
COPPER FLUOBORATE BATH		U	U		A	U			A	U	U	C		A	B	A		
COPPER STRIKE BATH			A			A			A	A	C	A		A	A	A		
COPPER SULFATE BATH		U	A			U			A	A	A	A		A	A	A		
COPPER-TIN BRONZE BATH		A	A		A	A			A	A	U	B		A	A	A		
COPPER-ZINC BRONZE BATH		A	A		A	A			A	A	C	A		A	A	A		
CYANIDE BATH		A	A			A			A	A	C	A		A	A	A		
FERROUS AMMONIUM SULFATE BATH						U			A	A	A			A	A	A		
FERROUS SULFATE BATH						A			A	A					A	A		
FLUOBORATE BATH		A	U		A	A			A	U	U	C			B	A		
FLUORIDE BATH		U	C			U			U	C	B	U		A	U	A		
FLUOSILICATE BATH		C	C			U			C	U	A	U		A	U	A		
GOLD PLATE BATH						A			A	A				A	A	A		
LEAD FLUOBORATE BATH						U			A	U	U				B	A		
NICKEL FLUOBORATE BATH						U			A	U					B	A		
ROCHELLE & POTASSIUM SALT BATH						A			A	A	U	B		A	A	A		
ROCHELLE & SODIUM SALT BATH									A	A	U	B		A	A	A		
RHODIUM BATH						U			U	U	A				A	A		
SILVER PLATE BATH						A			A	A	B			A	A	A		
SULFATE-CHLORIDE BATH						U			U	A					B	A		
TIN FLUOBORATE BATH						U			A	U	U			A	B	A		
POLYVINYL ACETATE														A			A	
POLYVINYL ACETATE EMULSION														A			A	A
POTASH		C	B		A	A			A		A	C			A	A		
POTASSIUM ACETATE														A	B	U	A	A
POTASSIUM BICARBONATE		U	U		A	A			B	B	A	C		A	A	A		A
POTASSIUM BORATE						A					A	B		A	A	A		
POTASSIUM BROMATE						A					A	A		A	A	A		
POTASSIUM BROMIDE		C	U	U	A	A			B	A	A	A		A	A	A	A	
POTASSIUM CARBONATE	U	U	A		A	A			B	A	A	B		A	A	A		A
POTASSIUM CHLORIDE	C	C	B	B	A	A		U	A	A	A	A		A	A	A	A	A
POTASSIUM CHROMATE		A	A			A			A		U	C		A	A	A	A	A
POTASSIUM CUPRO CYANIDE	U	U	A		B	B		U	B	A	A	C		A	A	A	A	
POTASSIUM CYANIDE	U	U	A	B	A	A		U	A	A	A	C		A	A	A	A	A
POTASSIUM DICHROMATE	U	U	A	C	A	A		U	B	A	B	C		A	A	A	A	A
POTASSIUM FERROCYANIDE		A			B	A			A	A				A	A	A	A	
POTASSIUM HYDROXIDE		U	C		A	A			A	B	A	U		A	B	U	A	A
POTASSIUM NITRATE		A			A	A			B	A	A	B		A	A	A	A	A
POTASSIUM PERFLUOROACETATE														A	A			A

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELIRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
POTASSIUM PERMANGANATE	C	C	A		A	A			A	A	A	C		A	A	A	A	
POTASSIUM PHOSPHATE	C	C	U		A	A								A	A			A
POTASSIUM SILICATE														A	A			A
POTASSIUM SULFATE	C	C	B	B	A	B		U	B	A	A	B		A	A	A	A	A
POTASSIUM SULFITE					B	A				A				A	A	A	A	A
PRESTONE		A			A	A									A	C		
PRODUCER GAS															A	A	U	
PROPANE (NEEDS HIGH INLET PRESSURE)*	A	A	A	B	A	A		A	B	A	A	B		A	A	A	U	A
PROPIONIC ACID	C													A		U		A
PROPION – ALDEHYDE														A				
PROPYL ACETATE														A	U	U	B	A
N-PROPYL ACETONE														A	U	U	A	A
PROPYL ALCOHOL	A	A						A						A	A	A	A	A
PROPYL NITRATE														A	U	U	B	A
PROPYLENE														A	U	A	U	A
PROPYLENE DICHLORIDE														A	U	A		A
PROPYLENE GLYCOL		A	B	B	B	A					A			A	A	A		A
PROPYLENE OXIDE															U	U	B	A^
PYDAUIS		A	A			A										A		
PYRIDINE		U	A	A	C	C			B	B	A	A		A	U	U	B	A
PYROGALLIC ACID		B			B	A			B	A	A	U		A		A		
PYROLIGNEOUS ACID		C				C									U	U	B	A
PYRANOL															A	A	U	
PYRROLE															U	U	C	A
QUATERNARY AMMONIUM GERMICIDE		U	U			A												
RAPESEED OIL		A	A		A	A				A	A	U		A	B	A	A	
RED OIL		C	C			A										A		
ROSE OIL					A	A								A	A	A		
ROSIN	C	A		C	A	A			A		A	B		A	A	A		
RUM		A			A	A					A	A		A	A	A		
RUST INHIBITORS	A	A	A		A	A		A			A	A		A	A	A		
SAL AMMONIAC		U			U	C			B					A	A	A	A	A
SALICYLIC ACID	C	C			C	C			A					A	B	A	A	A
SALT SOLUTION		A			A	A			A	A	A	A		A	A	A	A	
SESAME SEED OIL		A	A		A	A				A	A	U		A	A	A		
SEA WATER		B			A	A		C	A	A	A	A		A	A	A	A	A
SESAME OIL		A	A			A										A		
SEWAGE		A	A		A	A								A	A	A		
SHAVE CREAM		A			A	A								A	A	A		
SHELLAC	A	A	A	A	A	A		A			A	A		A	A			A
SILICA GEL		U	A			A								A				
SILICATE ESTERS														A	B	A	U	A
SILICONE OIL, GREASE	A	A	A		A	A		A	A		A	A		A	A	A	A	A
SILICONE TETRACHLORIDE														A		A		A

Legend	Materials											Plastics			Elastomerics			
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
SILVER BROMIDE					U	B			A			C		A				A
SILVER NITRATE		U	U	U	A	A			B	A	A	A		A	B	A	A	A
SILVER SALTS	U	U			A	A		U						A	A			
SIZING STARCH														A	A			
SKYDROL® 500		A			A	A									U	U	A	A
SKYDROL® 7000		A			A	A									U	B	A	A
SOAP SOLUTIONS	A	B	A	A	A	A		A	B	A	A	A		A	A	A	A	
SODA ASH (SODIUM CARBONATE)	A	A	A		A	B		A	B	A	A	A		A	A	A	A	A
SODA, CAUSTIC (20%)	C	C			A	A		A						A	U	U	A	
SODA, CAUSTIC (50%)	U	U			C	C								A	A	U		
SODIUM ACETATE		B	C	C	C	C			A	A	A	B		A	B	U	A	A
SODIUM ALUMINATE		A		C	A	A			B	B	A	B		A	A	A	A	A
SODIUM ARSENITE		U	U		A	A								A				A
SODIUM BICARBONATE	C	C	C	C	A	A		A	B	A	A	A		A	A	A	A	A
SODIUM BICHROMATE						A			A					A	A			A
SODIUM BISULFATE (HYPO)	C	C	U	U	A	A		A	B	B	A	B		A	A	A	A	A
SODIUM BISULFITE	C	C	U		A	A		A	B	A	A	B		A	C	A	A	A
SODIUM BORATE		A	C	C	A	A			A	A				A	A	A	A	A
SODIUM CARBONATE – ABRASIVE	A	A	B	B	A	B		A	B	A	A	A		A	A	A	A	A
SODIUM CHLORATE		A		C	A	A			A	A	A	A		A	B	A	A	
SODIUM CHLORIDE	C	B	B	C	A	A		C	A	A	A	A		A	A	A	A	A
SODIUM CHROMATE	A	A	B	B	A	A		A	B		A	U		A	A	A		A
SODIUM CITRATE						A			A					A				
SODIUM CYANIDE	U	U	B	B	A	A		U	A	A	A	A		A	A	A	A	A
SODIUM FLUORIDE		C	U	U	C	C			A	A	A	A		A	U	C		
SODIUM HYDROSULFITE		C							A		A			A	A	A		A
SODIUM HYDROXIDE (20%)	U	U	A		A	A		A	A	A	B	A		A	A	A	A	A
SODIUM HYDROXIDE (50%)	U	C	B		A	A		A	A	A	B	C		A	U	A	A	A
SODIUM HYPOCHLORITE >20%	U	U	U		C	C			A	A	A	U		A	C	A	B	
SODIUM HYPOCHLORITE		U	U	U		A			A	C	U	U		A	B	U		
SODIUM HYPOSULFATE		U			A	A								A				
SODIUM METAPHOSPHATE	C	C	B	B	A	A					A	B		A	A	A	A	A
SODIUM METASILICATE		B	C	C	A	A			A			U		A	A	A	A	
SODIUM NITRATE	C	B	A	B	A	A		A	C	A	A	A		A	C	A	A	A
SODIUM NITRITE		C	A		A	A			A					A	A	A		
SODIUM ORTHOPHENYLPHENATE					A	A								A	U			
SODIUM PERBORATE		U	C	B	C	C			B		A	B		A	B	A	A	A
SODIUM PEROXIDE	C	C	U	C	A	A		C	B		A	U		A	C	A	A	A
SODIUM PHOSPHATE-MONO	A	A	U		C	C		A	A	A	A			A	A	A	A	A
SODIUM PHOSPHATE-DI	C	C	A		A	A		C	A	A	A			A	A	A	A	A
SODIUM PHOSPHATE-TRI	U	U	A		A	A			A	A	A			A	A	A	A	A
SODIUM POLYPHOSPHATE		C	A		A	A			A	A	A	B		A	A	A	A	
SODIUM SILICATE – ABRASIVE	A	A	A	B	A	A		A	A	A	A	C		A	A	A	A	A
SODIUM SULFATE	C	C	A	B	A	A		A	B	A	A	B		A	A	A	A	A

Legend	Materials											Plastics			Elastomerics			
Chemical	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD, CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
A - GOOD																		
B - FAIR																		
C - QUESTIONABLE																		
U - UNSATISFACTORY																		
(See Legend Page for Details)																		
SODIUM SULFIDE	C	C	A	B	A	A		C	B	A	A	B		A	A	A	A	A
SODIUM SULFITE	C	C	A		A	B		C	A	A	A			A	A	A	A	A
SODIUM TETRABORATE					A	A					A	B		A	A	A		A
SODIUM THIOSULFATE	U	U	C		B	A		C	A	A	A	C		A	B	A	A	A
SODIUM TRIPOLYPHOSPHATE		U	U			A								A	A			
SOLUBLE OIL	A	A			A	A		A						A	A	A		
SORGHUM		U	A		A	A					A	A		A	A	A		
SOY BEAN OIL		A	A		A	A			A	A	A	U		A	A	A	C	A
SOY SAUCE		A	U		A	A					A	A		A	A	A		
SPERM OIL	A	A	A		A	A		A		A	A	U		A	A	A		
STANNIC CHLORIDE	U	U	U	U	U	U		U	B	A	U	C		A	A	A	A	
STANNIC FLUOBORATE		U	U			A					A	C		A	A	A		
STANNOUS CHLORIDE		U	U	U	U	C			A	A				A	A	A	A	A
STARCH	A	A	C	C	A	A		A			A	A		A	A	B		
STEARIC ACID	C	A	C	C	A	A		C	B	A	A	A		A	C	A	B	A
STEMRIC ACID	A				A	A		A						A	A	A		
STODDARD SOLVENTS	A	A	A	A	A	A		A	A	A	A	A		A	A	A	U	A
STYRENE	A	A		A	A	A		A	U		A	A		A	U	B	U	A^
SUGAR SOLUTIONS	A	A	B	B	A	A		A	A		A	A		A	A	A		
SULFATE LIQOURS	U	U	U		C	C		C	A		A	U		A				
SULFITE LIQOURS														A	B	A	B	A
SULFUR, MOLTEN		U			A	A		U	A					A	U	A	A	A
SULFUR BASED CUTTING OIL	A	A	A		A	A		A						A	A			
SULFUR CHLORIDE	C	C	U		U	U		C	B	U	C	U		A	U	A	U	A
SULFUR DIOXIDE GAS*	C	C			C	C		C	C	A	A	B		A	U	A	A	A
SULFUR HEXAFLUORIDE														A	B	B	B	B^
SULFUR TRIOXIDE	A	A	B	B	C	C		A	B	U	A	U		A	U	A	B	A
SULFURIC ACID (10%)	U	C	U		C	C		U	A	A	C	U		A	C	A	U	A
SULFURIC ACID (75%)	U	U	U		U	U		U	B	C	U	U		A	U	A	C	A
SULFURIC ACID-FUMING	U	C	U		U	U		U	C					A	U	A		
SULFUROUS ACID	U	U	U	U	C	C		U	B	A	A	C		A	B	A	B	A
SULFONATED FATTY ALCOHOLS														A				
SULFONATED VEGETABLE OILS														A	A			A
SYNTHETIC DETERGENT	C	C			A	A		A						A	A			
TALLOW-HOT	A	A			A	A		A			A	A		A	A	A		A
TANNIC ACID	A	B	C	C	C	C		A	B	A	A	B		A	A	A	A	A
TANNING LIQOURS	A	A			A	A		A	A	A	A	B		A	C	A		
TANNING OIL		A			A	A					A	U			A	A		
TAR	A	A			A	A		A			A			A	B	A	C	A
TARTARIC ACID	A	A	U	U	C	C		A	B	A	A	B		A	C	A	B	A
TERPINEOL															B	A	C	
TERTIARY BUTYL ALCOHOL						A			A	A	A			A	B	A	B	A
TERTIARY BUTYL CATECHOL														A	U	A	B	A
TERTIARY BUTYL MERCAPTAN														A	U	A	U	A

Legend	Materials											Plastics			Elastomerics			
Chemical	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD, CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELTRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ® ,CHEMREZ® (KPFE)
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)																		
TETRA BROMOMETHANE														A	U	A	U	A
TETRABUTYL TITANATE														A	B	A	A	A
TETRACHLOROETHANE	C	C	C		A	A			A	A	A	A		A	U	A		
TETRACHLOROETHYLENE												A			U	A	U	
TETRAETHYL LEAD		A	A		A	A								A	B	A	U	A
TETRAHYDROFURAN		U	U	A	A	A			A	B	A	A		A	U	U	C	A
TETRALIN®											A				U	A	U	
THIONYL CHLORIDE		U	U			U								A	U	B	C	A
TITANIUM TETRACHLORIDE														A	B	B	U	B^
TOLUENE (TOLUOL)	A	A	A	A	A	A		A	A	A	A	C		A	U	C	U	A
TOLUENE DI-ISOCYANIDE														A	U	U	B	A
TOMATO PULP	A	A	C	C	A	A		A	A		A	B		A	A	A		
TRANSFORMER OIL		A	A		A	A					A	A		A	A	A		
TRANSFORMER PYRANOL	A	A			A	A		A						A	U	A		
TRANSMISSION FLUID TYPE A	A	A	A		A	A		A			A			A	A	A	U	A
TRIACETIN															B	U	A	
TRI-ARYL PHOSPHATE														A	U	A	A	A
TRIBUTOXY ETHYL PHOSPHATE														A	U	A	A	A
TRIBUTYL MERCAPTAN														A	U	A	U	A
TRIBUTYL PHOSPHATE														A	U	U	B	A
TRICHLOROACETIC ACID		U	U		U	U			B		A			A	B	C	B	A^
TRICHLOROBENZENE														A		A		A
TRICHLOROETHANE		C	C		C	A			A	A	A	A		A	U	C	U	A
TRICHLOROETHYLENE	A	A	C	B	A	A		A	A	B	A	B		A	U	A	U	A
TRICHLOROPANE		A	A			A								A	U	A		
TRICHLOROPROPANE	A	A	A		A	A		A	A		A	A		A	A	A		A
TRICRESYL PHOSPHATE		A				A			A	B	A	C		A	U	A	v	A
TRIETHANOLAMINE		A							A		A	U		A	B	U	A	A^
TRIETHYLALUMINUM														A	U	U	C	A
TRIETHYLBORANE														A	U	A	C	A
TRIETHYLPHOSPHATE						A			A					A				
TRI-FLUORO-VINYL CHLORIDE														A		A		
TRINITROTOLUENE														A	U	B	U	A
TRI-NORMAL-BUTYL PHOSPHATE														A	A			
TRIOCTYL PHOSPHATE														A	U	B	A	A
TRIPOLY PHOSPHATE														A				
TRISODIUM PHOSPHATE														A	A			A
TRICRESYL PHOSPHATE		A				A			A					A	U	C	U	A
TRIPHENYL PHOSPHATE						B												
TUNG OIL					A	A			A					A	A	A	C	A
TURBINE OIL		A	A		A	A				A	A	U		A	B	A	U	
TURPENTINE	A	A	B	B	A	A		A	A	B	A	A		A	A	A	U	A
UNSYMMETRICAL DIMETHYL HYDRAZINE															B	U	A	A
UREA FORMALDEHYDE														A	A			

Legend	Materials										Plastics			Elastomerics				
A - GOOD B - FAIR C - QUESTIONABLE U - UNSATISFACTORY (See Legend Page for Details)	BRASS (BB)	NICKEL ALUM.BRNZ. (NAB)	CAST IRON (F)	CARBON STEEL (CBST)	304 STAINLESS STEEL (S)	316 STAINLESS STEEL (SS)	DUPLEX STAINLESS (SSD)	CHROME PLATED ROD,CYL. (SCP)	HASTELLOY 'C'® (HC)	TITANIUM (TI)	CERAMIC (ALUMINIA) (CC)	ACETAL RESIN-DELRIN® (D)	POLYVINYLIDENE FLUORIDE (PVDF)	TEFLON® (PTFE)	BUNA-N (NBR)	VITON® (FPM)	ETHYLENE PROPYLENE DIENE MONOMER (EPDM)	KALREZ®,CHEMREZ® (KPFE)
Chemical																		
URINE	C	C	A		A	A					A	A		A	A	A		
VARNISH	A	A	C	C	A	A		A	A		A	A		A	B	A	U	A
VEGETABLE OIL	A	A	C		A	A		A			A	A		A	A	A	C	A
VERSILUBE															A	A	A	
VINEGAR	C	C	C	U	A	A		C	A	A	A	B		A	C	C	A	
VINYL CHLORIDE																A	B	
VINYL PYRIDINE														A			A	A
VINYLDENE CHLORIDE														A			A	A
VISCOSE														A	A			
VITRIOL OIL														A			A	A
WATER, BOILER-TREATED	A	A			A	A		A						A	C	U		
WATER, DEIONIZED		U			A	A			A					A				
WATER, DISTILLED	A	C	U		A	A		A	A	A	A	C		A	A	A	A	A
WATER, SALT	A	A	U		A	A		A	A	A	A	A		A	A	A	A	A
WATER BASED SOLUBLE OIL	A	A			A	A		A						A	A	A		
WHISKEY & WINES		A	U	U	A	A				A	A	A		A	A	A	A	
WHITE GAS														A				
WHITE LIQUOR		U	C		A	A		C	A		A	U		A	A	A		
WHITE PINE OIL															B	A	U	
XYLENE		A	A	B	A	A			A	A	A	A	A	A	U	A	U	A
XYLIDENES															C	U	U	
XYLOL	A	A			A	A		A						A	U	A		A
YEAST						A								A	A			
ZEOLITE														A	A			
ZINC ACETATE														A	B	U	A	A
ZINC AMMONIUM CHLORIDE														A				A
ZINC CHLORIDE	C	C	U	U	C	C		C	B	A	A	C		A	A	A	A	
ZINC CYANIDE														A	A			A
ZINC HYDROSULFITE		U	U		A	A					A	C		A	A		A	A
ZINC NITRATE	C	B	C	U	A	A			B	A	A			A	A	A	A	A
ZINC PHOSPHATE SOLUTION														A				A
ZINC SALTS														A				A
ZINC SULFATE	C	A	C		A	A		C	B	A	A	C		A	A	A	A	A
maximum viscosity 500 centipoise centistokes X specific gravity = centipoise																		